

## NR-SBR/A 9506 with insert

NR-SBR, black - commercial
Standard quality 70 Shore, for minor demands
Insert: glass fibre mesh, strength 300 N/50 mm (EN ISO 13934)

Hardness [Shore A]:	70 ±7
Density [g/cm <sup>3</sup> ]:	approx. 1.46
Tensile strength [N/mm <sup>2</sup> ]:	4
Elongation at break [%]:	200
Ozone resistance:	non resistant
Weather resistance:	non resistant
Oil resistance:	non resistant
Benzine resistance:	non resistant
Acid resistance:	moderately resistant
Strong bases:	moderately resistant
Abrasion resistance:	non suitable

### WORKING TEMPERATURE RANGE

Medium	dyn. (stat.)	max.	short-term
Air	-10 (-30) °C	+70 °C	+90 °C

### COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	70 °C	40 %

### ROTA-CURED SHEETS

Article nr.	Thickness mm	Width m	Length m	Surface	No. of insert.
4011 07151	1.5	1.4	20	SS	1
4011 07201	2.0	1.4	20	SS	1
4011 07301	3.0	1.4	10	SS	1
4011 07302	3.0	1.4	10	SS	2
4011 07401	4.0	1.4	10	SS	1
4011 07402	4.0	1.4	10	SS	2
4011 07501	5.0	1.4	10	SS	1
4011 07502	5.0	1.4	10	SS	2
4011 07601	6.0	1.4	10	SS	1
4011 07602	6.0	1.4	10	SS	2
4011 06801	8.0	1.4	5	SS	1
4011 06802	8.0	1.4	5	SS	2
4011 06001	10.0	1.4	5	SS	1
4011 06002	10.0	1.4	5	SS	2

S = smooth

